



## The Course of O<sub>2</sub> Partial Pressure and Electric Potential Across an Oxide Electrolyte Cell

Mogensen, Mogens Bjerg; Jacobsen, Torben

*Published in:*  
Meeting Abstracts - Electrochemical Society

*Publication date:*  
2008

*Document Version*  
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

*Citation (APA):*  
Mogensen, M. B., & Jacobsen, T. (2008). The Course of O<sub>2</sub> Partial Pressure and Electric Potential Across an Oxide Electrolyte Cell. In *Meeting Abstracts - Electrochemical Society* (pp. Abstract 381). The Electrochemical Society.

---

### General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

The course of O<sub>2</sub> partial pressure and electric potential across an oxide electrolyte cell

M. Mogensen<sup>1</sup>, T. Jacobsen<sup>2</sup>

<sup>1</sup>Fuel Cell and Solid State Chemistry Department  
Risø - DTU, P.O. Box 49, DK - 4000 Roskilde, Denmark  
<sup>2</sup>Department of Chemistry, Building 2006, The Technical  
University of Denmark, DK-2800 Lyngby, Denmark

INTRODUCTION

The basic theory for the description of solid oxide cells is in principle well developed; see e.g. the book of J. Maier [1]. In spite of this, well-respected authors are regularly publishing papers, which give erroneous conclusions, e.g. build-up of extremely high pressures of oxygen pressures inside an electrolyte if a cell is bad [2]. The reason for the errors is not always clear, and thus, it seems useful to do a detailed presentation of the course of the relevant potentials across the cell, such as the electrical potential, the electrochemical potential of electrons, and the oxygen partial pressure in pores (if present) in the electrolyte.

ARGUMENTS AND RESULTS

As in cells with liquid electrolytes there is an electrical double layer at both electrode/electrolyte interfaces. The electrical potential has in general a large jump at such an interface. In case of an unloaded cell all of the potential difference of about 1 V is taking place at the two interfaces. This is a consequence of the fact that there is no change in the oxygen stoichiometry across the electrolyte of a solid oxide cells (SOFC) using good oxide ion conducting electrolytes such as yttria stabilized zirconia (YSZ). This is in turn known from the fact that YSZ is thermodynamic stable over a potential difference of about 2 V. Thus, the course of the potential across an SOFC at open circuit voltage (OCV) looks in principle like in Figure 1 with no electrical potential gradient inside the electrolyte.




Figure 1. The course in principle of the electrical potential across an SOFC at OCV. t is the electrolyte thickness.

When SOFC is loaded the situation looks as in Fig. 2. The supply of electrons through the external current decreases the potential at the cathode and the O<sub>2</sub>-reduction “pushes” extra O<sup>2-</sup>-ions into the electrolyte, which locally becomes more negative. The equivalent oxidation process makes the electrolyte more positive next to the anode. Thus, the potential difference, which drives the O<sup>2-</sup>-ions through the electrolyte, is created.




Figure 2. The course in principle of the electrical potential across a solid oxide fuel cell under an electrical load with a significant current density. The slope of the line inside the electrolyte is determined by the current density and the ionic conductivity of the electrolyte only. t is the electrolyte thickness.

It is noted that all solid electrolytes will have a small electron conductivity. The local oxygen partial pressure (in small pores) through the electrolyte is determined by the electrochemical potential of the electrons. This is the potential that goes into the Nernst equation in order to calculate the oxygen pressure; not the electrical potential. In the full paper more detailed examples of the quantitative potential courses will be given for zirconia based SOFCs.

REFERENCES

- [1] J. Maier, Physical chemistry of ionic materials, Ions and electrons in solids, John Wiley and Sons, Chichester, GB (2004).
- [2] A.V. Virkar, *J. Power Sources*, **172**, 713–724 (2007).

ACKNOWLEDGEMENTS

This work was supported by Danish Programme Committee for Energy and Environment via the Strategic Electrochemistry Research Center (SERC) – contract no 2104-06-0011.